
| | |
|-----------|---|
| Product | LiTFSI:PYR13TFSI 1:9 (mol.) + 5wt% FEC + 5wt% VC |
| Quality | 99,9% |
| Reference | E179 |

| Analytic method | Unit | Specifications | |
|--------------------|------|----------------|-------|
| | | Min | Max |
| Composition | | | |
| LiTFSI | wt% | 6,02 | 7,02 |
| PYR13TFSI | wt% | 82,48 | 84,48 |
| FEC | wt% | 4,95 | 5,05 |
| VC | wt% | 4,95 | 5,05 |
| Karl Fisher | | | |
| Water content | ppm | ≤ 20 | |